


Technical Data Sheet

StoCrete TG 108

Screed material, polymer-modified, cementitious,
layer thickness 20-80 mm



Characteristics

Area of application

- for levelling unevenness in floor; for producing a slope; as a sub-base for a wearing layer in buildings (e.g. balcony); and on surfaces subject to vehicle traffic

Properties

- can be quickly over-coated
- polymer-modified, cementitious screed material (PCC/RC)
- low shrinkage and low residual stress

Information/notes

- product is in accordance with EN 1504-3
- always apply a finishing coat
- as a concrete repair product for the application case PCC I
- Only on surfaces subject to vehicle traffic in non-regulated scope (ZTV-ING)

Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Bulk density of fresh mortar	EN 1015-6	2.2 kg/dm ³	
Maximum particle size		6 mm	
Bond strength (28 days)	EN 1542	> 2.0 MPa	
Compressive strength	EN 12190	53 MPa	
Flexural strength	TP BE-PCC	8 MPa	
Static modulus of elasticity	EN 13412	23 GPa	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Substrate

Requirements

Requirements on the substrate:

The concrete substrate must be load-bearing and free from native and foreign substances that could interfere with adhesion, as well as from corrosion-promoting components (e.g. chlorides). Remove less strong layers and laitance.

Damp in accordance with the definition in the DAfStb (German) Repair Guideline 2001-10.

Preparation grade of the exposed reinforcing steel after substrate preparation: Sa 2½ in accordance with EN ISO 8501-1.

Technical Data Sheet

StoCrete TG 108

Average bond strength: 1.5 N/mm²
 Bond strength, lowest single value: 1.0 N/mm²

Preparations	<p>Prepare the substrate using a suitable mechanical process, such as abrasive blasting or high-pressure water blasting (> 800 bar). Bevel the edges of the areas of spalling under approx. 45°.</p> <p>Note: Rework any treated surfaces using a suitable process (abrasive blasting) if the substrate preparation process has led to joint faults in the area of the remaining existing concrete close to the surface. These can result from chiselling, knocking, milling, or flame cleaning.</p>
---------------------	---

Application

Application temperature	<p>Lowest application temperature: +5 °C Highest application temperature: +30 °C</p>
--------------------------------	---

Time for application	<p>At +5°C: approx. 35 minutes at +23 °C: approx. 20 minutes At +30 °C: approx. 15 minutes</p>
-----------------------------	--

Mixing ratio	<p>25 kg of material in accordance with the description / 2.75 l of water = 1.0 : 0.11 parts by weight Sto silo technology: Set the amount of water flow to approx. 290 l water / h</p>
---------------------	--

Material preparation	<p>Compulsory mixer: Decant water, then add the pre-blended dry mortar. Mix for approx. 2 minutes, allow to mature for approx. 3 minutes, and then mix again for approx. half a minute.</p> <p>Sto silo technology: mixing tube / 2-stage mixing shaft / subsequent mixing with a compulsory mixer.</p>
-----------------------------	---

Consumption	Type of application	Approx. consumption
	per mm layer thickness	2.0 kg/m ²
<p>Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.</p>		

Coating build-up	<p>1) Substrate preparation 2) Protection against corrosion: StoCrete TK (in case of exposed reinforcement) 3) Mineral bonding agent with StoCrete TH 200 4) Concrete repair with StoCrete TG 108 Layer thickness: 20 - 80 mm, partially up to 100 mm</p>
-------------------------	---

Technical Data Sheet

StoCrete TG 108

Higher layer thicknesses are possible due to multi-layer work.

Application

can be manually mixed using Sto silo technology and conveyed with a screed pump

1) Substrate preparation

Derust the exposed reinforcing steel in accordance with DIN EN ISO 12944-4 up to preparation grade Sa 2½. The derusted reinforcing steel must be free from dust and grease.

2) Protection against corrosion

Immediately after derusting of the reinforcing steel in accordance with EN ISO 12944, Part 4, coating with StoCrete TK is carried out in two application cycles. The reinforcing steels are coated uniformly without gaps using a paint brush.

Waiting time between the two application cycles is 4.5 hours.

The protection against corrosion must be sufficiently hardened on the reinforcing steel so that it cannot detach from the reinforcing steel during the second application cycle.

First application cycle: StoCrete TK grey Consumption approx. 130 g/m one-time application Ø to 18 mm

Second application cycle: StoCrete TK light grey consumption approx. 140 g/m one-time application Ø to 18 mm

or

First application cycle: StoCrete TK grey consumption approx. 150 g/m one-time application Ø above 18 mm

Second application cycle: StoCrete TK light grey consumption approx. 160 g/m one-time application Ø above 18 mm

3) Bonding agent

Pre-wet the concrete substrate sufficiently before applying the StoCrete TH 200 bonding agent (about 24 hours before the first application cycle).

At the time of application, however, the concrete substrate must be dry to the point that it just appears slightly damp.

Apply the StoCrete TH 200 bonding agent with pressure using a suitable tool such as a paint brush or brush.

Remove any cured bonding agent by abrasive blasting and renew it.

Consumption approx. 1.9 kg/m²

4) Concrete repair product/PCC screed

Apply StoCrete TG 108 as a concrete repair product / PCC screed onto the fresh mineral bonding agent StoCrete TH 200; spread it; compress it; trowel it off rough for the next coating. To ensure a good adhesive bond, always work wet on wet.

Consumption approx. 22 kg/m² per cm of layer thickness (mixed material)

Technical Data Sheet

StoCrete TG 108

Apply using a mason's trowel, square trowel, shovel. Then compact by tamping, trowel off with a float, and use a plasterer's float (e.g. Dallusch) for finishing the surface.

On larger surfaces, the material can be applied with a vibrating beam screed. If doing so, test in advance.

For multi-layer installation (layer thicknesses over 8 cm), do not trowel the preceding layer smooth. If it is, lightly blast the surface. Reapply the bonding agent.

5) Curing

curing procedure:

- a) Cover with film or sheeting
- b) Spray with water
- c) Chemical curing

Under normal conditions, curing must last at least 3 days. Observe the relevant standard DIN 1045-3:2012-03, the B8 data sheet "Nachbehandlung und Schutz des jungen Betons" (4.2014) published by the Verein Deutscher Zementwerke e.V., and ZTV-ING (2014/12) (available in German only).

Note:

Chemical curing may only be carried out if the subsequent work is compatible with this.

It is not possible to achieve a uniform colour shade of the mortar surface for procedural reasons.

The foil must not touch the surface of the mortar.

A key part of curing is adequately wetting the concrete substrate before applying the mortar, so that the substrate is water-saturated and the fresh mortar does not extract mixing water.

Note:

Please note: Before coating, blast the surface (shot-blasting).

Manual application:

with a mason's trowel, square trowel and shovel, screeding level, spirit level, plasterer's float (e.g. Dallusch), if required a power trowel and screed blade.

Silo and mixing technology:

Mixing occurs in the silo.

Mixing interruption at +25 °C: max. 30 min.

Remix with a compulsory mixer. Duration: approx. 0.5 minutes.

If conveying with a screed pump:

Remix with a screed pump. Duration: 0.5 minutes

Vessel pressure of the screed pump: 4 - 7 bar.

Technical Data Sheet

StoCrete TG 108

Hose diameter: 50 mm.
Feeding length: 50 - 80 m.
Feeding height: up to 30 m.

Cleaning the tools Clean with water immediately after use. Hardened material can only be removed mechanically.

Notes, recommendations, special information, miscellaneous The declaration(s) of performance can be obtained from the StoCretec Technisches InfoCenter
General application instructions are available at www.stocretec.de and in the notes of the latest Technical Manual.

Delivery

Packaging sack

Article number	Name	Container
02352-001	StoCrete TG 108	25 kg bag

Storage

Storage conditions Store in dry conditions.

Storage life In the original container until ... (see packaging).
This product has a low chromate content.
The product quality is best guaranteed in its unopened original container until its shelf life has expired. The first digit of the batch number is the final digit of the year. The second and third digits indicate the calendar week. Example: 1450013223 - shelf life until end of calendar week 45 in 2021.
For further explanation, see the price list.

Identification

Product group Screed materials

Safety This product is subject to compulsory labelling in accordance with the current EU regulation.
You will receive an EU Safety Data Sheet with your first order.
Please observe the information regarding the handling of the product, its storage, and disposal.

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless

Technical Data Sheet

StoCrete TG 108

responsible for establishing the product's suitability and use.
Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH
Gutenbergstr. 6
D-65830 Kriftel

Tel.: +49 6192 401-104
Fax: +49 6192 401-105
stocretec@sto.com
www.stocretec.de