

Technical Data Sheet

StoCrete TH 200

Bonding agent, polymer-modified, cementitious



Characteristics

Area of application

- as bonding agent
- to ensure a permanent bond between the concrete substrate and the subsequent concrete repair system

Properties

- polymer-modified, cementitious bonding agent
- very good adhesive strength on a concrete substrate

Information/notes

- component of the StoCretec system in accordance with the DAfStb (German) Repair Guideline 2001-10
- product is in accordance with EN 1504-3

Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Bulk density of fresh mortar	EN 1015-6	1.9 kg/dm ³	
Bond strength (28 days)	EN 1542	> 2.0 MPa	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Substrate

Requirements

Requirements on the substrate:

The concrete substrate must be load-bearing and free from native and foreign substances that could interfere with adhesion, as well as from corrosion-promoting components (e.g. chlorides). Remove less strong layers and laitance.

Damp in accordance with the definition in the DAfStb (German) Repair Guideline 2001-10.

Preparation grade of the exposed reinforcing steel after substrate preparation: Sa 2½ in accordance with EN ISO 8501-1.

Average bond strength: 1.5 N/mm²
Bond strength, lowest single value: 1.0 N/mm²

Preparations

Prepare the substrate using a suitable mechanical process, such as abrasive blasting or high-pressure water blasting (> 800 bar).

Technical Data Sheet

StoCrete TH 200

Open pores and blow-holes sufficiently.

Bevel the edges of the areas of spalling under approx. 45°.

Note:

Rework any treated surfaces using a suitable process (abrasive blasting) if the substrate preparation process has led to joint faults in the area of the remaining existing concrete close to the surface. These can result from chiselling, knocking, milling, or flame cleaning.

Application

Application temperature Lowest application temperature: +5 °C
 Highest application temperature: +30 °C

Time for application At +5 °C: approx. 90 minutes
 At +23 °C: approx. 60 minutes
 At +30 °C: approx. 45 minutes

Mixing ratio 25 kg of material in accordance with the description / 5.75 - 6.25 l water = 1.0 :
 0.23 - 0.25 parts by weight

Material preparation Compulsory mixer: decant water and add pre-blended dry mortar. Mix for approx. 2
 minutes. Allow to mature for approx. 3 minutes. Remix for approx. 30 seconds.

If using hand-held paddle mixers, they should be counter-rotating and interlocking. Ensure that the mixing paddles of the mixer are at least 1/3 of the diameter and and at least 2/3 of the height of the mixing container.

If using single mixing paddles, these must have two stirring rings that act using the principle of countercurrent flow. The speed should be up to approx. 500 rpm.

Consumption	Type of application	Approx. consumption	
	as bonding agent	1.6	kg/m ²

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

Coating build-up 1) Substrate preparation
 2) Protection against corrosion: StoCrete TK (in case of exposed reinforcement)
 3) StoCrete TH 200 bonding agent
 4) Concrete repair product/PCC screed with StoCrete LE or StoCrete TG 104, StoCrete TG 108, StoCrete TG 202, StoCrete TG 203, StoCrete TG 204

Application by paint brush, by brush

Technical Data Sheet

StoCrete TH 200

1) Substrate preparation

2) Corrosion protection

3) Bonding agent

Sufficiently wet the concrete substrate before applying StoCrete TH 200 (about 24 hours before the first application cycle).

However, when applying the product, the concrete substrate must be dry enough that it appears only slightly damp.

Apply the StoCrete TH 200 bonding agent with pressure using a suitable tool such as a paint brush or brush.

Remove any cured bonding agent by abrasive blasting and renew it.

Consumption approx. 1.6 kg/m² dry material

4) Concrete repair product/PCC screed

Then apply the already-mixed mortar (StoCrete LE or StoCrete TG 104, StoCrete TG 108, StoCrete TG 202, StoCrete TG 203, StoCrete TG 204) to the fresh bonding agent in accordance with the relevant Technical Data Sheet. To ensure a good adhesive bond, always work wet on wet.

Cleaning the tools

Clean tools with water immediately after use.

Notes, recommendations, special information, miscellaneous

The declaration(s) of performance can be obtained from the StoCretec Technisches InfoCenter

General application instructions are available at www.stocretec.de and in the notes of the latest Technical Manual.

Delivery

Packaging

sack

Article number

Name

Container

00416-001

StoCrete TH 200

25 kg bag

Storage

Storage conditions

Store in dry conditions.

Storage life

In the original container until ... (see packaging).

This product has a low chromate content.

The product quality is best guaranteed in its unopened original container until its shelf life has expired. The first digit of the batch number is the final digit of the year. The second and third digits indicate the calendar week. Example:

1450013223 - shelf life until end of calendar week 45 in 2021.

For further explanation, see the price list.

Technical Data Sheet

StoCrete TH 200

Certificates/approvals

Z-74.11-88

StoCretec PCC II.1 System
National technical approval

Identification

Product group

Bonding agent

Safety

This product is subject to compulsory labelling in accordance with the current EU regulation.

You will receive an EU Safety Data Sheet with your first order.

Please observe the information regarding the handling of the product, its storage, and disposal.

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use. Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH
Gutenbergstr. 6
D-65830 Kriftel

Tel.: +49 6192 401-104
Fax: +49 6192 401-105
stocretec@sto.com
www.stocretec.de