

EP primer for damp substrates

 €+^{30°C} ↓



Characteristics	
Area of application	 interior and exposed to the weather on floors capillary and pore waterproofing of cementitious substrates as a priming coat on non-mineral substrates such as stainless steel flanges and existing load-bearing epoxy resin coatings as a priming coat on balconies
Properties	 very good adhesive bond on mineral substrates and stainless steel contains de-airing additives
Appearance	• transparent
Information/notes	 product is in accordance with EN 1504-2 product is in accordance with EN 13813

Technical data

Criterion	Standard / test specification	Value/ Unit Notes
Bond strength (28 days)	EN 1542	> 2,0 MPa
Viscosity (at 23 °C)	EN ISO 3219	750 - 950 mPa.s mixture
Density (mixture 23 °C)	EN ISO 2811	1,03 - 1,09 g/cm³

the natural raw materials in our products, the stated values on approximate values. Due to same delivery batch; this does not affect the suitability of the product for its intended use.

C 11	het	101	5
ou	051	e	

Requirements

Requirements on the substrate:

The substrate can be dry or damp, but must be load-bearing and free from native and foreign substances that have a separating action. Remove less strong layers and laitance.

Dry or damp in accordance with the definition in the DAfStb (German) Repair Guideline 2001-10 $\,$

Substrate temperature higher than +10 °C and 3 K above dew point.



	Average bond strength: 1.5 N/mm ² Bond strength, lowest single value: 1.0 N/mm ²		
	Stainless steel surfaces SA 2 1/2 - metallic brig 12944-4.	ht in accordance with	I EN ISO
Preparations	Prepare the substrate using a suitable mechani milling and then shot-blasting, or abrasive blast	cal process such as a ing.	shot-blasting,
Application			
Application temperature	lowest application temperature: +10 °C Highest application temperature: +30 °C max. approved relative humidity: 85 %		
Time for application	At +10 °C: approx. 50 minutes At +20 °C: approx. 25 minutes at +30 °C: approx. 10 minutes		
Mixing ratio	component A : component B = 100.0 : 45.0 par	ts by weight	
Material preparation	Component A and Component B are supplied in the correct mixing ratio and should be mixed in accordance with the following instructions. Stir Component A, then add all of Component B. Mix thoroughly with a slow-running paddle mixer (max. 300 rpm) until a homogeneous, streak-free compound develops. It is also vital to stir thoroughly at the sides and the bottom in order to evenly distribute the hardener. Mixing time at least 3 minutes. Do not apply from the delivery container! After mixing, transfer the material into a clean container and stir it thoroughly one again. The temperature of the individual components must be min. +15 °C when mixing		atio and il a o evenly oroughly once when mixing.
Consumption	Type of application	Approx. cons	sumption
	as primer, depending on the substrate	0,3 - 0,6	kg/m²
	Material consumption depends on the application among other factors. The stated consumption v guide. If required, determine precise consumption specific project.	on, substrate, and con alues are only to be u on values on the bas	nsistency, used as a is of the
Coating build-up	 Substrate preparation Prime coating of StoPox 452 EP Scratch coat (optional, e.g. roughness > 0.5 Finishing coat 	mm)	



Application	1) Substrate preparation
	2) Prime coating Apply StoPox 452 EP with a rubber squeegee, flooding until the substrate is totally free of pores, and then evenly spread the material by rolling/brushing. Avoid forming puddles. Apply StoPox 452 EP primer in one or more application cycles depending on the substrate.
	Consumption: approx. 0.3 - 0.6 kg/m ² , depending on the roughness of the substrate
	If there is a waiting time of more than 72 hours until the next coating, lightly sand the prime coating and prime again or apply some scatter.
	Scatter with StoQuarz 0.1 - 0.5 mm
	Consumption: approx. 1.0 kg/m ²
	3) Scratch coat Prime with StoPox 452 EP.
	Consumption: approx. 0.3 - 0.6 kg/m ² and application cycle
	Apply a scratch coat, consisting of 1 part by weight StoPox GH 452 EP and up to 2 parts by weight StoQuarz 0.1 - 0.5 (StoDivers ST thixotropic additive can be added) on to the prepared and primed substrate.
	Apply the product using a smoothing trowel, a squeegee with triangular notching, and a spiked roller.
	Consumption of StoPox 452 EP: approx. 0.6 - 0.7 kg/m ² and mm of layer thickness
	Consumption of StoQuarz 0.1 - 0.5 mm: approx. 1.2 - 1.4 kg/m ² and mm of layer thickness
	consumption: approx. 1.0 - 3.0 kg/m ²
	4) Finishing coat e.g. StoPur EA or StoPur EB 200, StoPox KU 601 in accordance with the relevant Technical Data Sheets
Drying, curing, ready for next coat	Reworking time: At +10°C: approx. 28 h At +23°C: approx. 14 h At +30°C: approx. 10 h



Cleaning the tools	Clean with StoCryl VV.
Notes, recommendations, special information, miscellaneous	The declaration(s) of performance can be obtained from the StoCretec Technisches InfoCenter General application instructions are available at www.stocretec.de and in the notes of the latest Technical Manual. The abrasion resistance class specified in the CE marking refers to the smooth, not scattered covering.
Delivery	
Packaging	pail and tin

	Article number	Name	Container	
	14062/028	StoPox 452 EP Set	10 kg set	
	14062/027	StoPox 452 EP Set	4 kg set	
	14062/026	StoPox 452 EP Set	23 kg set	
Storage				
Storage conditions	Store in dry and frost-free conditions. Avoid direct sunlight.			
Storage life	In the original contain	ner until (see packaging).		

Identification	
Product group	Primer
GISCODE	RE30
Safety	This product is subject to compulsory labelling in accordance with the current EU regulation. You will receive an EU Safety Data Sheet with your first order. Please observe the information regarding the handling of the product, its storage, and disposal.
	(Practical guide for handling epoxy resins) and test report: "Prüfbericht zur Schutzwirkung von acht Chemikalienschutzhandschuhen gegenüber EP-Beschichtungen" (Test report on the protective effect of eight chemical protective gloves against EP coatings), Gloves: "Handschuhe für den Umgang mit lösemittelfreien Epoxidharzen" (Gloves for handling solvent-free epoxy resins), and Protective gloves: "Die richtige Anwendung von Schutzhandschuhen" (The correct

Rev. no.: 100 / EN /StoCretec./. 11.12.2023 / PROD0175 / StoPox 452 EP



use of protective gloves) Https://www.bgbau.de/themen/sicherheit-und-gesundheit/gefahrstoffe/umgangmit-epoxidharzen/

Published by: BG BAU - Berufsgenossenschaft der Bauwirtschaft Hildegardstraße 29/30, 10715 DE-Berlin Tel. (+49) 30 85781-0, Fax. (+49) 800 6686688-37400, www.bgbau.de

Guidelines for the planning of building site facilities: "Wirtschaftliche and sichere Baustelleneinrichtung"

Published by: Bundesanstalt für Arbeitsschutz und Arbeitsmedizin (BAuA) Friedrich-Henkel-Weg 1-25, 44149 DE-Dortmund Tel. (+49) 231 9071-0, Fax. (+49) 231 9071-2454, E-mail: poststelle@baua.bund.de, homepage: www.baua.de

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH Gutenbergstr. 6 D-65830 Kriftel

Tel.: +49 6192 401-104 Fax: +49 6192 401-105 stocretec@sto.com www.stocretec.de