


# Technical Data Sheet

## StoPur PM MultiBase

PUR coating for increased requirements, tested and approved surface protection systems for traffic structures



### Characteristics

<b>Area of application</b>	<ul style="list-style-type: none"> <li>• interior</li> <li>• exposed to the weather</li> <li>• as a coating for floor areas subject to vehicle traffic in multi-storey car parks and underground car parks</li> <li>• as the main effective surface protection layer in the surface protection system: OS 10.4 of StoCretec</li> </ul>
----------------------------	--

<b>Properties</b>	<ul style="list-style-type: none"> <li>• highly elastic</li> <li>• solvent-free</li> <li>• plasticiser-free</li> <li>• proportion consists of renewable resources</li> </ul>
-------------------	--

<b>Information/notes</b>	<ul style="list-style-type: none"> <li>• product is in accordance with EN 1504-2</li> <li>• product is in accordance with EN 13813</li> </ul>
--------------------------	---

### Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Shore hardness type A	EN ISO 868	85	(28 days)
Viscosity (at 23 °C)	EN ISO 3219	4,000 - 5,000 mPa.s	mixture
Density (mixture 23 °C)	EN ISO 2811	1.42 g/cm <sup>3</sup>	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

### Substrate

<b>Requirements</b>	<p>General:</p> <ul style="list-style-type: none"> <li>- Dry, load-bearing</li> <li>- Free from separating, native, or foreign substances</li> <li>- Remove weak layers.</li> <li>- Remove any accumulation of fine concrete particles on the surface.</li> </ul>
---------------------	---

## Technical Data Sheet

### StoPur PM MultiBase

**Dry substrate:**

- Depends on the compressive strength class
- Dry according to the definition contained in the DAfStb (German) Repair Guideline, issue 2001-10.

**Moisture content:**

- Measure the moisture content of the concrete substrate with a calcium carbide meter.
- Moisture content for concrete qualities up to C30/37: max. 4 CM per cent
- Moisture content for concrete qualities up to C35/45: max. 3 CM per cent

Substrate temperature: at least +12 °C, 3 K above the dew point  
Bond strength, average: 1.5 N/mm<sup>2</sup>

Bond strength, lowest single value: 1.0 N/mm<sup>2</sup>

**Preparations**

1) Prepare all the above-mentioned substrates using a mechanical method, see "Substrate, requirements".

**Example:**

- Shot-blasting
- Milling followed by shot-blasting
- Abrasive blasting

**Application****Application temperature**

substrate and air temperature  
minimum temperature: +10 °C  
maximum temperature: +30 °C

Application temperature:  
minimum temperature: +10 °C  
maximum temperature: +30 °C

Relative humidity:  
minimum: 30 %  
maximum: 80 %

**Time for application**

at +23 °C: approx. 20 minutes

**Mixing ratio**

component A : component B  
A : B  
100.0 : 19.0 parts by weight

**Material preparation****Notes:**

- Component A and component B are supplied in the correct mixing ratio and should be mixed in accordance with the following instructions.
- Observe the order of the "Preparing material" steps.

## Technical Data Sheet

### StoPur PM MultiBase

- The material temperature is between +15 °C and +25 °C.
- The temperature of all components is between +15 °C and +25 °C.

#### Mixing time:

- The length of the mixing time depends on the temperature of the material and the ambient temperature.
- Mix each container for the same length of time.

#### Possible consequences if mixing times are too long or too short:

- Mixing the product too long will shorten the time for application.

#### Preparing the material:

- 1) Stir component A.
- 2) Add all of component B.
- 3) Mix the components until the hardener is well distributed, the mixture is homogeneous, and a streak-free mass is produced.  
Paddle mixer: slow running mixer, max. 300 rpm  
Mixing time: at least 3 minutes
- 4) Ensure the the mixing equipment covers the floor areas and the edge zones of the mixing container. The hardener must be evenly distributed.
- 5) Transfer the mixture to a clean container. Mix the components again.

#### Coating build-up

- 1) Prepare the substrate.
- 2) Priming: StoPox GH 500
- 3) Scatter: StoQuarz 0.3-0.8 mm
- 4) Apply a crack-bridging, elastic floating layer: StoPur PM MultiBase
- 5) Applying a wearing course: StoPur AC MultiCoat
- 6) Optionally, scatter: StoQuarz 0.3–0.8 mm or 0.6-1.2 mm
- 7) Optionally, seal: StoPur DV 506

#### Application

- 1) Prepare the substrate.
- 2) Priming:
  - StoPox GH 500
  - Apply the product evenly. Tools: rubber squeegee
  - Rework the product and spread evenly with a roller.
  - consumption: approx. 0.3-0.4 kg/m<sup>2</sup>, depending on the roughness of the substrate
  - Note: Avoid the formation of puddles.
  - Recommendation: Apply a scratch coat for roughness depths > 0.5 mm.
- 3) Scatter:
  - StoQuarz 0.3-0.8 mm
  - Scatter the fresh priming coat grain by grain without any surplus.
  - consumption: approx. 0.5 - 1.0 kg/m<sup>2</sup>
  - Note: Remove the unbound quartz sand after 24 h.

# Technical Data Sheet

---

## StoPur PM MultiBase

4) Apply a crack-bridging, elastic floating layer, main effective surface protection layer:

- StoPur PM MultiBase
- Apply the product unfilled without quartz sand. layer thickness: at least 2.0 mm, tool: squeegee with triangular notching
- Rework the product in a criss-cross pattern for ventilation. Tools: spiked roller
- consumption: approx. 3.0 kg/m<sup>2</sup>
- Note: use spiked soles with straight-edged nails during scattering or de-airing to prevent damage to the membrane.

5) Applying a wearing course:

- StoPur AC MultiCoat
- Waiting time: Apply the wearing course after 8-24 hours.
- Apply the self-levelling mortar in the required layer thickness.
- consumption of StoPur AC MultiCoat: approx. 2.5 kg/m<sup>2</sup>

6) Optionally, scatter:

- StoQuarz 0.3–0.8 mm or 0.6-1.2 mm
- Scatter the surface full-faced in excess.
- consumption of StoQuarz 0.3-0.8 mm or 0.6-1.2 mm: approx. 1-2 kg/m<sup>2</sup>

7) Optionally, seal:

- StoPur DV 506
- Remove the unbound quartz sand.
- Apply the product evenly in a criss-cross pattern. Tools: rubber squeegee
- Rework the product and spread evenly in a criss-cross pattern with a roller.
- Tools: short-pile roller sleeve
- consumption: approx. 0.6-1.0 kg/m<sup>2</sup>, depending on the scattering

Apply the StoCretec surface protection system OS 10.4:

- Consumption and details: implementation instructions, attachment 1 of the general building inspection test certificate.

Notes:

- Damp and not fully cured substrates lead to damage.
- Substrate temperature, ambient temperature:
  - In addition to the environment temperature, the substrate temperature is vital for the application of reaction resins.
  - Low temperatures delay the chemical reactions.
  - This extends the time for application, overcoating, and walking on it.
  - The consumption per surface unit may rise due to increasing viscosity.
  - High temperatures accelerate chemical reactions, reducing the time for application, overcoating, and walking on it.

Colour shade deviation:

- Exposure of the chemicals may cause discolourations, which do not, however, impair the technical function of the coating.

# Technical Data Sheet

## StoPur PM MultiBase

- Slight deviations in the colour shade are possible between different batches.

Consumption, application:

- The details on consumption and application relate to horizontal surfaces.
- On inclinations: test a sample surface area first. If required, work in multi-layers and add thixotropic additive or more quartz sand to the materials.

### Drying, curing, ready for next coat

Time until the area is suitable for foot traffic:

- After approx. 8 hours
- Reworking time:
- at +23 °C: within 24 hours

### Cleaning the tools

Clean tools with StoDivers EV 100 or StoCryl VV.

### Notes, recommendations, special information, miscellaneous

- 1) Observe the general application instructions:
  - see [www.stocretec.de](http://www.stocretec.de), Products
  - see technical manual, notes
- 2) Observe the implementation instructions.

Declaration of performance, CE marking:

- declaration of performance: see [www.stocretec.de](http://www.stocretec.de)
- The abrasion resistance specified in the declaration of performance refers to the smooth, not scattered covering.

### Delivery

Colour shade                      grey

Packaging                         pail

Article number	Name	Container
09725/001	StoPur PM MultiBase Set	25 kg set

### Storage

**Storage conditions**                      Store in dry and frost-free conditions. Protect from direct sunlight.

**Storage life**                                The product quality is best guaranteed in its unopened original container until its shelf life has expired. This information is included in the batch number on the container. Explanation of batch nos.:  
 digit 1 = last digit of the year, digits 2 + 3 = calendar week, example: 1450013223 - storage life ends at week 45 in 2022  
 See product packaging

### Identification

**Product group**                              Waterproofing

# Technical Data Sheet

---

## StoPur PM MultiBase

---

### Safety

This product is subject to compulsory labelling in accordance with the current EU regulation.  
Observe the Safety Data Sheet!

### Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.  
Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH  
Gutenbergstr. 6  
D-65830 Kriftel

Tel.: +49 6192 401-104  
Fax: +49 6192 401-105  
stocretec@sto.com  
www.stocretec.de