


# Technical Data Sheet

## StoPur SL 125

PUR pore filler, elasticised, low-emission



### Characteristics

**Area of application** • as a pore sealing filler for rubber granulate mats

**Properties** • moisture-proof during curing  
• optimum non-sag properties

### Substrate

#### Requirements

General:

- Dry, load-bearing
- Free from separating, native, or foreign substances
- Remove weak layers.
- Remove the scatter sand which has not been integrated.
- Remove any accumulation of fine concrete particles on the surface.

Dry substrate:

- Depends on the compressive strength class
- Dry according to the definition contained in the DAfStb (German) Repair Guideline, issue 2001-10.

Moisture content:

- Measure the moisture content of the concrete substrate with a calcium carbide meter.
- Moisture content for concrete qualities up to C30/37: max. 4 CM per cent
- Moisture content for concrete qualities up to C35/45: max. 3 CM per cent

Substrate temperature: at least +10 °C, 3 K above the dew point Bond strength, average: 1.5 N/mm<sup>2</sup>

Bond strength, lowest single value: 1.0 N/mm<sup>2</sup>

#### Preparations

1) Prepare all the above-mentioned substrates using a mechanical method, see "Substrate, requirements".

Example:

- Shot-blasting
- Milling followed by shot-blasting
- Abrasive blasting

### Application

**Application temperature** substrate and air temperature  
minimum temperature: +10 °C  
maximum temperature: +30 °C

## Technical Data Sheet

### StoPur SL 125

Application temperature:  
minimum temperature: +10 °C  
maximum temperature: +30 °C

Relative humidity:  
minimum: 30 %  
maximum: 90 %

<b>Time for application</b>	At +10 °C: approx. 60 minutes At +20 °C: approx. 45 minutes at +30 °C: approx. 30 minutes
<b>Mixing ratio</b>	component A : component B A : B 100.0 : 25.0 parts by weight
<b>Material preparation</b>	<p>Notes:</p> <ul style="list-style-type: none"><li>- Component A and Component B are supplied in the correct mixing ratio and should be mixed in accordance with the following instructions.</li><li>- Observe the order of the "Preparing material" steps.</li><li>- The material temperature is between +15 °C and +25 °C.</li><li>- The temperature of all components is between +15 °C and +25 °C.</li></ul> <p>Mixing time:</p> <ul style="list-style-type: none"><li>- The length of the mixing time depends on the temperature of the material and the ambient temperature.</li><li>- Mix each container for the same length of time.</li></ul> <p>Possible consequences if mixing times are too long or too short:</p> <ul style="list-style-type: none"><li>- Mixing the product too long will shorten the time for application.</li></ul> <p>Preparing the material:</p> <ol style="list-style-type: none"><li>1) Stir component A.</li><li>2) Add all of component B.</li><li>3) Mix the components until the hardener is well distributed, the mixture is homogeneous, and a streak-free mass is produced. Paddle mixer: slow running mixer, max. 300 rpm Mixing time: at least 3 minutes</li><li>4) Ensure the the mixing equipment covers the floor areas and the edge zones of the mixing container. The hardener must be evenly distributed.</li><li>5) Transfer the mixture to a clean container. Mix the components again.</li></ol>
<b>Coating build-up</b>	<ol style="list-style-type: none"><li>1) Prepare the substrate.</li><li>2) Priming: StoPox GH 500</li><li>3) Scatter: StoQuarz 0.3-0.8 mm</li><li>4) Adhesive layer: StoPur AL 125</li><li>5) Laying elastic rubber granulate mats.</li></ol>

## Technical Data Sheet

### StoPur SL 125

- 6) Closing pores: StoPur SL 125
- 7) Apply an optional levelling layer: StoPur CL 125
- 8) Coating: StoPur CL 125
- 9) Sealing: StoPur WV 202

#### Application

- 1) Prepare the substrate.
- 2) Priming:
  - StoPox GH 500
  - Flood apply the product. Tools: rubber squeegee
  - Rework the product with a roller and spread evenly.
  - consumption: approx. 0.2-0.3 kg/m<sup>2</sup>, depending on the roughness of the substrate
  - Note: Avoid the formation of puddles.
- 3) Scatter:
  - StoQuarz 0.3-0.8 mm
  - Scatter the fresh priming coat grain by grain without any surplus.
  - consumption: approx. 0.5-1.0 kg/m<sup>2</sup>
- 4) Applying the adhesive:
  - StoPur AL 125
  - Apply the product. Tools: spatula
  - Spread the product evenly.
  - consumption: approx. 0.3-0.8 kg/m<sup>2</sup>
  - Note: The applied material may not come into contact with water during the first 20 hours after application.
- 5) Laying elastic rubber granulate mats:
  - Lay the elastic rubber granulate mats with butt joints at the required height in StoPur AL 125.
  - Weigh down the elastic rubber granulate mats with weights at the ends and in the middle.
  - After approx. 30-60 minutes, depending on the temperature: rework the elastic rubber granulate mats to prevent any bubbles. Tools: installation roller, 50 kg
- 6) Closing pores:
  - StoPur SL 125
  - Apply the product. Tools: rubber squeegee or spatula
  - Spread the product evenly.
  - consumption: approx. 0.6-1.0 kg/m<sup>2</sup>
  - Note: The elastic rubber granulate mats must be dry and free of release agents.
- 7) Apply an optional levelling layer:
  - StoPur CL 125
  - Apply the product. Tools: squeegee
  - Spread the product evenly.

## Technical Data Sheet

### StoPur SL 125

- consumption: approx. 0.6-1.0 kg/m<sup>2</sup>

#### 8. Coating:

- StoPur CL 125
- Apply the product. Tools: squeegee
- Spread the product evenly and de-air. Tools: spiked roller
- consumption: approx. 1.8-2.5 kg/m<sup>2</sup>
- Note: The coating must be applied on the underlying layer within 24 hours.

#### 9) Sealing:

- StoPur WV 202
- Apply the product evenly in a criss-cross pattern. Tools: rubber squeegee
- Rework the product and spread evenly in a criss-cross pattern with a roller. Tools: short-pile roller sleeve
- consumption of StoPur WV 202: approx. 120-140 g/m<sup>2</sup>
- Note: Avoid the formation of puddles to prevent any difference in gloss level. Do not wait longer than five minutes between rolling on two strips of paint. Always work wet-on-wet to prevent initial drying at the edges.

#### Note:

- Avoid direct sunlight, high temperatures, and draughts during application.
- Exposure of the chemicals may cause discolourations, which do not, however, impair the technical function of the coating.
- When working with polyurethane, make sure that the material does not come into contact with water during curing, as this can lead to reaction bubbles (foam formation).
- Roller marks can occur with the sealing coat.
- Layer thickness of the sealing coat: < 0.5 mm. Mechanical use reduces the layer thickness. This can shorten the service life.
- Different material application, too high humidity, and low temperatures can lead to visual defects, e.g. differences in the gloss levels.

#### Cleaning the tools

Clean tools with StoDivers EV 100 or StoCryl VV.

#### Notes, recommendations, special information, miscellaneous

- 1) Observe the general application instructions:
  - see [www.stocretec.de](http://www.stocretec.de), Products
  - see technical manual, notes
- 2) Observe the implementation instructions.

#### Declaration of performance, CE marking:

- declaration of performance: see [www.stocretec.de](http://www.stocretec.de)
- The abrasion resistance specified in the declaration of performance refers to the smooth, not scattered covering.

#### Delivery

##### Packaging

pail

# Technical Data Sheet

## StoPur SL 125

Article number	Name	Container
04087/001	StoPur SL 125 Set	30 kg set

### Storage

**Storage conditions** Store in dry and frost-free conditions. Protect from direct sunlight. Avoid temperatures above +25 °C. Store in dry and frost-free conditions. Protect from direct sunlight.

**Storage life** The product quality is best guaranteed in its unopened original container until its shelf life has expired. This information is included in the batch number on the container. Explanation of batch nos.: digit 1 = last digit of the year, digits 2 + 3 = calendar week, example: 2450013223 - storage life ends at week 45 in 2022  
See product packaging The product quality is best guaranteed in its unopened original container until its shelf life has expired. The first digit of the batch number is the final digit of the year. The second and third digits indicate the calendar week. Example: 1450013223 - shelf life until end of calendar week 45 in 2021.  
See product packaging

### Identification

**Product group** Filler

**GISCODE** x

**Safety** This product is subject to compulsory labelling in accordance with the current EU regulation.  
Observe the Safety Data Sheet!

### Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.  
Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

## Technical Data Sheet

---

### **StoPur SL 125**

StoCretec GmbH  
Gutenbergstr. 6  
D-65830 Kriftel

Tel.: +49 6192 401-104  
Fax: +49 6192 401-105  
[stocretec@sto.com](mailto:stocretec@sto.com)  
[www.stocretec.de](http://www.stocretec.de)