

Technical Data Sheet

StoQuarz AS 300

Aggregate mixture with a specially matched grain size distribution for filling StoPma EB 300 and StoPma RZ 500



Characteristics

Area of application	<ul style="list-style-type: none"> as extender component for PMMA resins in accordance with the Technical Data Sheet
----------------------------	---

Application

Material preparation	<p>Stir liquid component thoroughly to evenly distribute the paraffin. Before adding the catalyst, stir StoQuarz AS 300 into the liquid component until the mixture is homogenous. Then add exactly the right amount of catalyst. Mix thoroughly with a slow-running paddle mixer (maximum 300 rpm). Mixing time at least 1 minute. Apply immediately.</p>
-----------------------------	--

Consumption	Type of application	Approx. consumption
	see Technical Data Sheet of the liquid component	

Application	add to the total mixture
--------------------	--------------------------

Delivery

Packaging	sack
------------------	------

Article number	Name	Container
01439-003	StoQuarz AS 300	20 kg bag

Identification

Technical Data Sheet

StoQuarz AS 300

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH
Gutenbergstr. 6
D-65830 Kriftel

Tel.: +49 6192 401-104
Fax: +49 6192 401-105
stocretec@sto.com
www.stocretec.de